

CERTEX

Vertical Blind Fabric Specification

KEY FEATURES:

Fabric composition:	100% Polyester
Fire retardancy:	EN 13773 : 2003 Class 1, BS5867 - 2, Type B : 2008 for fire retardancy when tested in accordance with BS5438 : 1989
Shading:	Dim-out - Recommended for computer environments
Moisture resistance:	Recommended for moist conditions

STANDARD SPECIFICATIONS:

Colour range:	19
Louvre widths available:	89mm (3 1/2"); 127mm (5")
Typical fabric weight:	340gsm (+/- 50)
Fabric thickness:	0.86mm - nominal
Colourfast:	Conforms to BS5867 - 1 : 2004 for light fastness to Grade 6 minimum when tested in accordance with ISO 105 - B02 : 1999
Care instructions:	Machine washable; Do not tumble dry; Do not dry clean; Do not iron

COLOUR	HEAT		LIGHT		S-C
	T	R	T	R	
Aubergine	2%	20%	2%	17%	0.35
Azure	5%	36%	1%	30%	0.33
Beige	13%	54%	11%	64%	0.30
Cream	13%	56%	13%	67%	0.29
Dark Beige	8%	46%	2%	44%	0.30
Dark Blue	1%	18%	1%	8%	0.35
Dark Green	1%	18%	1%	8%	0.35
Grey	7%	39%	1%	34%	0.32
Lavender	8%	46%	2%	44%	0.30
Light Blue	5%	36%	1%	30%	0.33
Light Green	8%	46%	2%	44%	0.30
Mid Blue	3%	25%	1%	17%	0.34
Mid Grey	7%	39%	1%	34%	0.32
Purple	2%	20%	2%	17%	0.35
Raspberry	2%	21%	1%	15%	0.34
Red	2%	21%	1%	15%	0.34
Terracotta	10%	50%	4%	50%	0.30
White	13%	58%	14%	75%	0.29
Yellow	13%	55%	12%	65%	0.30

This data is based on:

Tests conducted using double glazed 6mm float glass with 12mm air space. Blinds are fully closed.

Shading Co-efficients are calculated for radiation at normal incidence. Standard U value is 2.75 W/M 2k = 0.49Btu/ft2hx°F.

Important: Performance data has been compiled with great care using the latest techniques. However, it is advisable to check actual suitability of fabrics for a particular application before use.

In line with our commitment to product development, specifications may be subject to change without notice.

T = % Transmitted : R = % Reflected : S-C = Shading Co-efficient. Shading Co-efficients are expressed as a decimal between 0 and 1. The lower the figure, the higher the shading efficiency of the blind.



SK Systèmes
Unit A1
Yelverton Business Park
Yelverton
Devon
PL20 7PE

Tel : +44 (0)1822 859 178
Fax : +44 (0)1822 854 344
E-mail : sales@sksystemes.net
Web: www.sksystemes.net