

QUARTZ

Vertical And Roller Blind Fabric Specification

KEY FEATURES:

Fabric composition:	100% Fibreglass
Fire retardancy:	Conforms to: BS5867 - 2, Type B : 2008 for fire retardancy when tested in accordance with BS5438 : 1989. Classement au Feu ininflammable M2 AFNOR NFP 92-503 Schwer Entflammbar Nach DIN 4102 Part 1 B1.
Shading:	Standard - Suitable for computer environments
Moisture resistance:	Suitable for moist conditions

STANDARD SPECIFICATIONS:

Colour range:	6
Louvre widths available:	89mm (3 1/2"); 127mm (5")
Roller fabric width:	180cm (72") nominal
Typical fabric weight:	260gsm (+/- 10)
Fabric thickness:	0.38mm - nominal
Colourfast:	Conforms to BS5867 - 1 : 2004 for light fastness to Grade 6 minimum when tested in accordance with ISO 105 - B02 : 1999
Care instructions:	Wipe with damp sponge; Do not wash; Do not tumble dry;

COLOUR	HEAT		LIGHT		S-C
	T	R	T	R	
Beige	25	38	38	50	0.51
Blue	32	40	12	20	0.65
Cream	25	38	38	50	0.51
Grey (vertical only)	30	38	43	54	0.55
Optic White	24	35	39	52	0.49
Yellow	27	35	39	51	0.52

T = % Transmitted : R = % Reflected : S-C = Shading Co-efficient. Shading Co-efficients are expressed as a decimal between 0 and 1. The lower the figure, the higher the shading efficiency of the blind.

This data is based on:

Tests conducted using double glazed 6mm float glass with 12mm air space. Blinds are fully closed.

Shading Co-efficients are calculated for radiation at normal incidence. Standard U value is 2.75 W/M 2K = 0.49Btu/ft2hxF.

Important: Performance data has been compiled with great care using the latest techniques. However, it is advisable to check actual suitability of fabrics for a particular application before use.

In line with our commitment to product development, specifications may be subject to change without notice.



SK Systèmes
Unit A1
Yelverton Business Park
Yelverton
Devon
PL20 7PE

Tel : +44 (0)1822 859 178
Fax : +44 (0)1822 854 344
E-mail : sales@skssystemes.net
Web: www.skssystemes.net



Beige



Grey



Blue



Optic White



Cream



Yellow